

# CARATTERISTICHE TECNICHE

TECHNICAL FEATURES













CARACTÉRISTIQUES TECHNIQUES

TECHNISCHE MERKMALE

## GRES PORCELLANATO

PORCELAIN STONEWARE • GRÈS CÉRAME • FEINSTEINZEUG

UNI EN 14411 BIA ALLEGATO G (ISO 13006)

Caratteristica tecnica Technical feature Caractéristique technique Technische Eigenschaft	Norma Norm Norme Norm	Valore richiesto dalle norme Required standards Valeur prescrite par les normes Normvorgabe	Serie Emotion
 <b>Assorbimento d'acqua</b> Water absorption Absorption d'eau Wasseraufnahme	UNI EN ISO 10545-3	≤ 0,5%	≤ 0,5%
 <b>Resistenza alla flessione</b> Bending strength Résistance à la flexion Biegefestigkeit	UNI EN ISO 10545-4	≥ 35 N/mm <sup>2</sup>	<b>Conforme</b> Corresponding Conforme Entsprechend
 <b>Resistenza al gelo</b> Resistance to frost Résistance aux gel Frostbeständigkeit	UNI EN ISO 10545-12	<b>Nessuna alterazione</b> No alteration Aucune alteration Keine Veränderung	<b>Non gelivo</b> Frost-proof Non gélifs Frostsicher
 <b>Caratteristiche di regolarità</b> Regularity characteristics Caractéristiques de régularité Regelmäßigkeit	UNI EN ISO 10545-2	<b>Lunghezza e larghezza</b> / Length and width Longuer et largeur / Länge und breite	± 0,6% max
		<b>Spessore</b> / Thickness Epaisseur / Stärke	± 5% max
		<b>Rettilineità spigoli</b> / Straightness of sides Rectitude des arêtes / Kantengeradheit	± 0,5% max
		<b>Ortogonalità</b> / Rectangularity Orthogonalité / Rechtwinkligkeit	± 0,6% max
		<b>Planarità</b> / Length and width Planeité de surface / Ebenfächigkeit	± 0,5% max
 <b>Qualità della superficie</b> Surface quality Qualités de la surface Oberflächenqualität	UNI EN ISO 10545-2	<b>Il 95 % min. delle piastrelle di prova deve essere esente da difetti visibili</b> Minimum 95% of the tested tiles must be free from visible defects 95% min. des carreaux de test ne doit pas contenir de défauts visibles Min. 95% der geprüften Fliesen dürfen keine sichtbaren Mängel aufweisen	<b>Conforme</b> Corresponding Conforme Entsprechend
 <b>Resistenza ai prodotti chimici</b> Resistance to chemical products Résistance aux produits chimiques Widerstand gegen Chemikalien	UNI EN ISO 10545-13	<b>Minimo GB</b> Minimum GB Minimum GB Minimum GB	<b>Conforme</b> Corresponding Conforme Entsprechend
 <b>Resistenza all'abrasione (metodo PEI)</b> Wear resistance (PEI test) Résistance à l'abrasion (méthode PEI) Widerstand gegen Abrieb (nach PEI)	UNI EN ISO 10545-7	<b>Come dichiarato</b> As stated Comme déclaré Wie angegeben	Antracite Pei 4 Blanc, Gris, Taupe Pei 5
 <b>Resistenza alle macchie</b> Staining resistance Résistance aux taches Widerstand gegen Fleckenbildung	UNI EN ISO 10545-14	Min. 3	<b>Conforme</b> Corresponding Conforme Entsprechend
 <b>Stabilità dei colori</b> Colours stability Stabilité des couleurs Farbbeständigkeit	DIN 51094	<b>Stabile</b>	<b>Nessuna Variazione</b>
 <b>Durezza Superficie Mohs</b> Mohs surface hardness Dureté de la surface (échelle Mohs) Ritzhärte nach Mohs	UNI EN 101	<b>Come dichiarato</b> As stated Comme déclaré Wie angegeben	≥ 6
 <b>Resistenza agli sbalzi termici</b> Thermal shock resistance Résistance aux écarts de température Temperaturwechselbeständigkeit	ISO 10545-9	<b>Metodo di prova disponibile</b> Test method available Méthode d'essai disponible Prüfverfahren verfügbar	Resiste Resistant
 <b>Resistenza allo scivolamento</b> Slip resistance Résistance au glissement Rutschemmende Eigenschaft	METODO B.C.R.A.	D.M.I. Giugno 1989 n. 236 (μ > 0,40)	> 0,4
	DIN 51130	<b>In funzione dell'ambiente o della zona di lavoro</b> Basing on the environment or on the working area	60x60, 81x81 R9 31x31 R9 – R11